

TABLE III

Samples Taken by Ascot Metals (Robertson and Hainsworth, 1950)

Cu(%)	Au(oz/ton)	Ag(oz/ton)	Ni(%)	Comments
0.26	0.01	trace	nil	Trench 4, chip sample over 10 feet
0.25	trace	-	-	Trench 5, chip sample over 36 feet
0.28	trace	-	-	Trench 5, grab sample from dump
0.13	trace	-	-	Trench 6, chip sample over 11 feet
1.34	trace	0.13	nil	Trench 7, chip sample over 2 feet
1.02	trace	0.24	nil	Trench 7, chip sample over 15 feet
0.96	0.01	trace	nil	Trench 7, chip sample over 15 feet
1.16	0.01	0.40	nil	Trench 7, chip sample over 15 feet
1.12	0.01	0.12	nil	Trench 7, grab sample from dump
0.40	trace	0.16	nil	Trench 8, chip sample over 22 feet
0.36	trace	0.14	nil	Trench 8, grab sample from dump